



# FOUR R MARKETING, LLC

*“Your Supply Solution”*

## HH750

### Product Data Sheet

| Test Description                       | Test Method | Typical Values |
|--|-------------|----------------|
| Viscosity, cSt @ 40°C                  | ASTM D-445  | 144.7          |
| Viscosity, cSt @ 100°C                 | ASTM D-445  | 11.26          |
| Viscosity, SUS @100°F                  | ASTM D-2161 | 672            |
| Viscosity, SUS @ 210°F                 | ASTM D-2161 | 63.7           |
| API Gravity                            | ASTM D-287  | 21.7           |
| Pounds Per Gallon                      | ASTM D-1250 | 7.69           |
| Flash Point, Cleveland Open Cup, °F    | ASTM D-92   | 410            |
| Color                                  | ASTM D-1500 | 2.5            |
| Acid Number ,mg KOH/g                  | ASTM D-664  | 0.01           |
| Aniline point, F                       | ASTM D-611  | 202            |
| Sulfur wt. %                           | ASTM D-2622 | 0.074          |
| Refractive index, 20C (68F)            | ASTM D-1218 | 1.504          |
| UV Absorptivity at 260nm               | ASTM D-2008 | 4.53           |
| Clay-gel, wt. %                        | ASTM D-2007 |                |
| Asphaltenes                            |             | 0.21           |
| Polar Compounds                        |             | 3.16           |
| Aromatics                              |             | 37.20          |
| Saturates                              |             | 59.43          |
| Carbon Type Analysis                   | ASTM D-2140 |                |
| Ca                                     |             | 12             |
| Cn                                     |             | 36             |
| Cp                                     |             | 52             |
| Polycyclic Aromatic Compounds, (wt. %) | IP 346      | <3.0           |